


A



B

Fig. 14-2. Slump test for consistency of concrete. Figure A illustrates a low slump, Figure B a high slump.

For masonry grouting - "unless otherwise specified the desired consistency of grout shall be considered achieved when the slump falls between 8 and 11 inches."